

CONSUMER MANUAL

BENEFITS:

- Lasts longer in power hungry devices
- Reliable portable power



APPLICATIONS BEST FOR:









OTHER DETAILS:

- Alkaline Manganese Dioxide chemistry
- Average weight: 48g




9 Volts

ELECTRICAL CHARACTERISTICS

Test	Test Conditions 25 ± 2°C 60 ± 15%RH	Specification (Volt), min				
Items		3 months	1 year	3 years*	5 years*	
OCV		9.55V	9.30V	9.10V	8.90V	
CCV	47Ω, 0.3 s	8.65V	8.00V	7.70V	7.30V	

12.7±0.25



Unit: mm

DISCHARGE CAPACITY

Toot	Test Conditions 25 ± 2°C 60 ± 15%RH (EV=End Voltage)	Specification (Hours), mean				
Test Items		3 months	1 year	3 years*	5 years*	
	270 Ω Intermittent 1 h/d EV=5.40V	20.5	20.2	18.7	16.7	
Duration	620 Ω Intermittent 2 h/d EV=5.40V	49.0	47.5	45.0	44.0	
	10 kΩ background 24 h/d, 620 Ω 1 s/h pulse EV=7.50V	Specification (Days), mean				
		20.0	19.5	18.5	17.5	

^{*} Storage performance is estimated.

Model No.: GP1604AU